


AMENDMENTS TO THE CLAIMS

1. (Currently Amended) A high-brightness mechanoluminescence material consisting of a composite semiconductor crystal represented by the general formula




(in the formula, each of M^1 and M^2 is, independently from the other, an element selected from Zn, Mn, Cd, Cu, Eu, Fe, Co, Ni, Mg and Ca, each of A^1 and A^2 is an atom selected independently from chalcogens with the proviso that M^1A^1 and M^2A^2 differ each from the other, and x is a positive number smaller than 1[[.]])) and wherein the composite semiconductor crystal has a mixed structure of the wurtzite-type structure and the zincblende-type structure.

2. (Canceled)

3. (Original) The high-brightness mechanoluminescence material described in claim 1 in which M^1 is Mn or Eu and A^1 and A^2 are each the same chalcogen as the other.

4. (Original) The high-brightness mechanoluminescence material described in claim 1 in which M^2 is constituted of Zn, Cd or a combination of Zn and Cu.

5. (Original) A method for the preparation of the high-brightness mechanoluminescence material defined in claim 1, which comprises the steps of; mixing source materials of the constituent ingredients; heating the thus obtained mixture in vacuum at a temperature lower than the sublimation point of the product to produce a composition represented by the general formula



(in the formula, each of M^1 and M^2 is, independently from the other, an element selected from Zn, Mn, Cd, Cu, Eu, Fe, Co, Ni, Mg and Ca, each of A^1 and A^2 is an atom selected independently from chalcogens and x is a positive number smaller than 1, with the proviso that M^1A^1 and M^2A^2 differ each from the other); causing sublimation of the composition at a temperature equal to or higher

than the sublimation point of the composition; and crystallizing the thus generated sublimate by condensation at a temperature lower than the sublimation point thereof.